

GRAYSTAR LLC

*A Manufacturer and Distributor of
Abrasive Materials and Specialty Products*

Headquarters

9 Simmonsville Rd
PO Box 1670
Bluffton, SC 29910

Phone: 843-815-5600
Fax: 843-815-5601
www.graystarllc.com

FEPA F Standard

Grit Size Designation	D3% Value Max. (microns)	D50% Value (microns)	D94% Value Min. (microns)
F 240	70	42.5 - 46.5	28
F 280	59	35.0 - 38.0	22
F 320	49	27.7 - 30.7	16.5
F 360	40	21.3 - 24.3	12
F 400	32	16.3 - 18.3	8
F 500	25	11.8 - 13.8	5
F 600	19	8.3 - 10.3	3
F 800	14	5.5 - 7.5	2
F 1000	10	3.7 - 5.3	1
F 1200	7	2.5 - 3.5	1 (at D80%)

FEPA Standard 42-2: 2006, Table 1: Grain Size Distribution of Microgrits

Values apply to measurements by means of potosedimentometer. Graystar correlates the above values to a Coulter Multisizer in accordance to the referenced FEPA Standard,