

GRAYSTAR[★]LLC

Ceramic Minerals and Specialty Materials

Sales Office

8500 Sheridan Dr
Williamsville, NY 14221
Phone: 716-633-0077
Fax: 716-633-0099
Quality Manager: rprevite@graystarllc.com

Headquarters

9 Simmonsville Rd
PO Box 1670
Bluffton, SC 29910
Phone: 843-815-5600
Fax: 843-815-5601

FEPA F Standard

| Size | D3% Max. | D50% | D94% Min. |
|------|-------------|-----------|--------------|
| 240 | 70 | 42.5-46.5 | 28 |
| 280 | 59 | 35.0-38.0 | 22 |
| 320 | 49 | 27.7-30.7 | 16.5 |
| 360 | 40 | 21.3-24.3 | 12.0 |
| 400 | 32 | 16.3-18.3 | 8 |
| 500 | 25 | 11.8-13.8 | 5 |
| 600 | 19 | 8.3-10.3 | 3 |
| 800 | 14 | 5.5-7.5 | 2 |
| 1000 | 10 | 3.7-5.3 | 1 |
| 1200 | 7 | 2.5-3.5 | 1(80%) |

FEPA - Standard 42-GB-1984 Part 3-R, Table 1: Grain Size Distribution of Microgrits F230 to F1200.

Values apply to measurements by means of a photosedimentometer. Graystar correlates the above values to a Coulter Multisizer in accordance to the referenced FEPA standard.